

TECHNICAL SPECIFICATIONRef. **TSi 18917 en**

Issue date 21. 8. 2009

Page 1/1

Product AC SILPAP 2S - GL80R LL

Two-side siliconised brown glassine paper.

	Method	Unit	Typical values
Grammage	ISO 536	g/m ²	80
Thickness	ISO 534	µm	69
Moisture content	ISO 287	%	4,0
Tensile strength MD	ISO 1924-3	kN/m	8,0
Tensile strength CD	ISO 1924-3	kN/m	4,0
Release force, both sides	FTM 10	cN/25 mm	15
Subsequent adhesion	FTM 11	%	min. 80

All information is based on our existing knowledge and experience. Given properties are typical values. As the products are used for different applications we recommend checking product suitability prior to use.